



防窺膜規格書
Specification

產品名稱 Product Name : Privacy film

產品規格 Overall size : **2 way**: 280mm x 280mm , 370mm x 280mm

產品構造 Product Structure		<table border="1"> <tr><td>H/C PET</td></tr> <tr><td>Silicone Adhesive</td></tr> <tr><td>Silicone Inner Layer</td></tr> <tr><td>Silicone Adhesive</td></tr> <tr><td>PET Liner</td></tr> </table>		H/C PET	Silicone Adhesive	Silicone Inner Layer	Silicone Adhesive	PET Liner
		H/C PET						
Silicone Adhesive								
Silicone Inner Layer								
Silicone Adhesive								
PET Liner								
項目 Item	單位 Unit	檢查方法 Test Method	規格值 Spec. value					
有效厚度 Thickness	μm	Detected by Micrometer	400 ±10					
霧度 Haze	%	ASTM D1003-07	34.55					
透過率 Transmittance	%	ASTM D1003-07	≥ 62					
鉛筆硬度 Hardness		JIS K-5400/8.4	3H(3/5)					
黏著力(膠層對鋼板) Adhesion		JIS Z0237(2009)	0.022					
黏著力(PET對膠層) Adhesion		JIS Z0237(2009)	0.392					
耐高溫 Heat resistance		80°C , 50 hrs	無白化、剝離、脫膠、氣泡產生 No whitening、Peeling、Bubble					
耐高溫高濕 Humidity resistance		60°C 90%RH ,50 hrs	無白化、剝離、脫膠、氣泡產生 No whitening、Peeling、Bubble					

※有效厚度:不含離型膜度與保護膜。

4/20/2012

防窺膜規格書
Specification

產品名稱 Product Name : Privacy film

產品規格 Overall size : **4 way**: 280mm x 280mm

<p>產品構造 Product Structure</p>		<table border="1" style="margin-left: auto; margin-right: auto;"> <tr><td>H/C PET</td></tr> <tr><td>Silicone Adhesive</td></tr> <tr><td>Silicone Inner Layer</td></tr> <tr><td>Silicone Adhesive</td></tr> <tr><td>Silicone Inner Layer</td></tr> <tr><td>Silicone Adhesive</td></tr> <tr><td>PET Liner</td></tr> </table>		H/C PET	Silicone Adhesive	Silicone Inner Layer	Silicone Adhesive	Silicone Inner Layer	Silicone Adhesive	PET Liner
		H/C PET								
Silicone Adhesive										
Silicone Inner Layer										
Silicone Adhesive										
Silicone Inner Layer										
Silicone Adhesive										
PET Liner										
項目 Item	單位 Unit	檢查方法 Test Method	規格值 Spec. value							
有效厚度 Thickness	μm	Detected by Micrometer	600 ±10							
霧度 Haze	%	ASTM D1003-07	34.55							
透過率 Transmittance	%	ASTM D1003-07	≥ 62							
鉛筆硬度 Hardness		JIS K-5400/8.4	3H(3/5)							
黏著力(膠層對鋼板) Adhesion		JIS Z0237(2009)	0.022							
黏著力(PET對膠層) Adhesion		JIS Z0237(2009)	0.392							
耐高溫 Heat resistance		80°C , 50 hrs	無白化、剝離、脫膠、氣泡產生 No whitening、Peeling、Bubble							
耐高溫高濕 Humidity resistance		60°C 90%RH ,50 hrs	無白化、剝離、脫膠、氣泡產生 No whitening、Peeling、Bubble							

※有效厚度:不含離型膜度與保護膜。

4/20/2012